



silverdream®

Visionaire®

Metallic effects for
solvent-borne nail
polishes

A member of **ALTANA**

ECKART
Effect Pigments



Metallic effects for solvent-borne nail polishes

SILVERDREAM is dedicated to metallic pigment preparations for nail polishes. Besides standing out by luxurious and valorizing metallic look, the pigment preparations unfold additional attractiveness when combined with pearlescent pigments like MIRAGE or SYNCRYSTAL as well as colorants.

The Silverdream product line features impressive metallic highlights like Starlight, which represents captivating silver sparkle or Prismatic types, unique products made by PVD technology with outstanding rainbow-like appearance.

Silverdream Polaris – applied in combination with a special magnet – exhibits extra-ordinary three-dimensional effects thanks to the alignment of the iron flakes incorporated by magnetic forces.

VISIONAIRE shades are synonyms for superior performance, dramatic metallic reflection and excellent coverage.

Packaging

SILVERDREAM: 5 kg, 10 kg (Polaris also 25 kg)

VISIONAIRE: 1 kg, 5 kg, 10 kg

SILVERDREAM

| Type | Article No. | Particle Size (microns) | Content (%) | Iron Powder | Isopropyl Alcohol | Paraffinum Liquidum |
|--------------------------------------|-------------|-------------------------|--|-------------------------------------|-----------------------------------|-------------------------------------|
| | | | Aluminum Powder (CI 77000) CAS: 7429-90-5 EINECS: 231-072-3 | CAS: 7439-89-6 EINECS: 231-096-4 | CAS: 67-63-0 EINECS: 200-661-7 | CAS: 8042-47-5 EINECS: 232-455-8 |
| Metallic pigment preparations | | | | | | |
| Starlight 70 IL | 007302 | 20 – 95 | 68 – 72 | – | 28 – 32 | – |
| Polaris 90 WM | 052329 | 5 – 40 | – | 88 – 92 | – | 8 – 12 |
| Type | | | | Ethyl Acetate (%) | Acetone (%) | Butyl Acetate |
| | | | | CAS: 141-78-6 EINECS: 205-500-4 | CAS: 67-64-1 EINECS: 200-662-2 | CAS: 123-86-4 EINECS: 204-658-1 |
| Aluminum pigment dispersions | | | | | | |
| L-55350 | 056252ZZ268 | 11 – 12 | 10 | < 90 | < 3.10 | |
| Prismatic H-50550 | 052506ZZ168 | 48 – 52 | 5 | < 95 | < 4.00 | |
| Prismatic H-115002 | 053002ZZ168 | 100 – 150 | 0,40 – 0,52 | | 10 – 50 | 50 – 90 |

VISIONAIRE


| Type | Article No. | Particle Size (microns) | Content (%) | Silica | Red 34 (CI 15880) | Aluminum Hydroxide |
|---------------------------|-------------|-------------------------|--|-------------------------------------|-------------------------------------|--------------------------------------|
| | | | Aluminum Powder (CI 77000) CAS: 7429-90-5 EINECS: 231-072-3 | CAS: 7631-86-9 EINECS: 231-545-4 | CAS: 6417-83-0 EINECS: 229-142-3 | CAS: 21645-51-2 EINECS: 244-492-7 |
| Silver shades | | | | | | |
| Silver Sea | 040444 | 5 – 50 | 85 – 95 | 5 – 15 | | |
| Bright Silver Sea | 040443 | 15 – 70 | 85 – 95 | 5 – 15 | | |
| Sparkling Silver Sea | 040966 | 20 – 95 | 85 – 95 | 5 – 15 | | |
| Special shades | | | | | | |
| Bright Splendid Red 34 | 041711 | 15 – 70 | 75 – 83 | 13 – 17 | 4 – 8 | – |
| Bright Splendid Champagne | 021094 | 15 – 70 | 58 – 73 | 5 – 10 | – | 22 – 32 |

silverdream®

Visionaire®



Special shades



Bright Splendid Red 34 15-70 µm Article No. 041711



Bright Splendid Champagne 15 – 70 µm Article No. 021094

Metallic pigment preparations



Starlight 70 IL

20 – 95 µm

Article No. 07302




Polaris 90 WM

(Example of Application)

5 – 40 µm


Article No. 052329



L-55350 11 – 12 μm Article No. 056252ZZ268



Prismatic H-50550 48 – 52 μm Article No. 052506ZZ168



Prismatic H-115002 100 – 150 μm Article No. 053002ZZ168

Silver shades



Silver Sea

5 – 50 µm

Article No. 040444



Bright Silver Sea

15 – 70 µm

Article No. 040443



Sparkling Silver Sea

20 – 95 µm

Article No. 040966



ECKART GmbH
Guentersthal 4
91235 Hartenstein, Germany
Tel +49 9152 77-0
Fax +49 9152 77-7008
info.eckart@altana.com
www.eckart.net

ECKART America Corporation
830 East Erie Street
Painesville, Ohio 44077, USA
Tel +1 440 954 7600
Fax +1 440 354 6224
Toll-free 866 458 7837
info.eckart.cosmetics@altana.com
www.eckart.net

ECKART Asia Ltd.
Unit 3706-08, 37/F, Sunlight Tower
248 Queen's Road East
Wan Chai, Hong Kong
Tel +852 3102 7200
Fax +852 2882 5366
info.eckart.asia@altana.com
www.eckart.net

2/March2016.1 COS
099174XX0

This information and our technical advice – whether verbal, in writing or by way of trials – are given in good faith but without warranty, and this also applies where proprietary rights of third parties are involved. Our advice does not release you from the obligation to verify the information currently provided – especially that contained in our safety data and technical information sheets – and to test our products as to their suitability for the intended processes and uses. The application, use and processing of our products and the products manufactured by you on the basis of our technical advice are beyond our control and, therefore, entirely your own responsibility.